



## **CA-RX3**

### **RETARDER - INTESIFIER**

#### **DESCRIPTION**

CA-RX3 is a temperature extender for Messina's cement retarder, CA-R10A and other selected retarders. Its properties are:

Form	White Granules
Specific Gravity	1.75
Bulk Density	65 lbs/cu ft

#### **APPLICATION**

The addition of CA-RX3 retarder aid will extend the temperature range of CA-R10A and other lignosulfonate-based retarders up to 282°C (550°F).

#### **RECOMMENDED TREATMENT**

CA-RX3 is normally recommended for use with lignosulfonate-based retarders at ratios from 1:1 to 3:1 (retarder:CARX3).

CA-RX3 can be dry-blended with the cement or added to the cement mix water. Pilot testing with actual cement, water, and additives to be used in the field is always recommended due to the high temperatures for which this product is designed.

#### **HANDLING**

CA-RX3 is a moderate eye irritant. Goggles should be worn while handling. In case of eye contact, flush with water for 15 minutes.

#### **PACKAGING**

CA-RX3 is available in 50 pound sacks.

